

630PA





Product Overview

Crestafix 630PA is pre-accelerated vinylester based high performance bonding paste. It is a non-sagging, filled compound with high strength, specifically designed for the assembly and bonding of GRP mouldings. Such applications include panels, inserts, internal frames, ribs, internal core materials and composite constructions. Crestafix 630PA provides high shear-strength bonded joints without the need for mechanical fixings.

Features and Benefits

Highly thixotropic High strength Vinyl ester base No sagging on vertical surfaces

Replaces mechanical fastners

Excellent adhesion and good elongation at break

Application Properties

Working Time¹ 50 - 70 Minutes

Fixture Time² 180 - 240 Minutes

Gap Filling 1 - 25 mm (0.04 - 1.0 inch)

Colour Change Deep Purple to Brown

Mechanical Properties

 GRP Lap Shear Strength³
 6.5 MPa (substrate failure)

 Tensile Strength⁴
 50 - 60 MPa (7250 - 8700 psi)

 Tensile Modulus⁴
 3.3 - 3.7 GPa (475,000 - 535,000 psi)

 Tensile Elongation⁴
 2.5 - 3.5 %

 Hardness
 80 - 90 Shore D

 HDT
 60°C (140°F)

Liquid Properties

Viscosity ⁵ 6.0 s-1 Viscosity ⁵ 0.6 s-1	90,000 - 130,000 cP 950,000 - 1,300,000 cP
Specific Gravity	1.05 - 1.15 g/cc
Colour	Deep Purple
Shelf Life ⁶	3 Months

Recommended Substrates

Crestafix 630PA is suitable for use on GRP laminates, but also can be used on timber and plasterboard. However it is recommended that trials are carried out to ensure adequate bond strengths are obtained. Please contact Scott Bader Technical Services for information on other substrates and advice.

Surface Preparation

The surfaces to be bonded should be clean, dry and free from any contamination. It may be necessary to mechanically abrade the surfaces to be bonded in order to obtain the bond strength required. Please contact Scott Bader Technical Services for information on other substrates and advice.

Application

Crestafix 630PA is supplied pre-accelerated, requiring only the addition of catalyst to start the curing reaction. The recommended catalyst is Triganox 239 (or other equivalent catalyst e.g. Butanox LPT-IN), which should be added at 2% v/w into the bonding paste. The catalyst should be thoroughly incorporated into the material with a low shear mechanical stirrer where possible, taking care to keep air entrapment to a minimum. The bonding paste, moulding and workshop should all be at, or above, 15° C (59° F) before curing is carried out. Recommended temperature range for application is between 18° C and 25° C (64° F and 77° F). Each surface should be coated with the catalysed bonding paste and held together until the adhesive has hardened.

The use of additional pigments or fillers is not recommended as they can affect the performance of the adhesive.

For industrial/commercial use only. The user must determine the suitability of a selected adhesive for a given substrate and application. Contact your local Scott Bader representative for questions or assistance with the selection of adhesives for your use. This product is intended for use by skilled individuals at their own risk. Recommendations contained herein are based on information we believe to be reliable. The properties and strength values have been obtained under controlled conditions at the Scott Bader laboratory.

Coverage

As a rough guide, 3.3Kg (7.2lbs) of bonding paste will cover one square metre (10.76 ft²) to a depth of approximately 3mm (0.1 inch).

Storage & Shelf life

Crestafix 630PA should be stored between 2°C and 23°C (36°F and 77°F) in the original unopened container in a dry, well ventilated place. Protect from freezing and direct sunlight. Avoid contact with oxidising agents.

The shelflife is defined from date of manufacture when stored as recommended. The expiry date is indicated on product labels.

Packaging

Crestafix 630PA is supplied in 25Kg (55lbs) and 225Kg (496lbs) containers.

Health and Safety

See separate Material Safety Data Sheet.

Notes

1 Working Time measured with 100g mass of adhesive with 2% Triganox 239 at 25°C (77°F)

2. Fixture time defined using an ISO-4587 GRP lap shear sample, 3 mm bondline thickness with 23°C (73°F) ambient temperature achieving >1.4MPa.

3. As tested to BS ISO 4587

4. As tested to BS EN ISO 527-2.

5. Measuring using Rotovisco 1 (RV1) at 25°C (77°F) 35mm PF

6. The shelf life is defined from date of manufacture if stored as recommended.



© 2018 ScottBader Co Ltd, May 2019

Scott Bader UK

Wollaston, Wellingborough, Northants NN29 7RL, UK

Tel: +44 (0)1933 666738

Email: enquiries@scottbader.com

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.